

ECO HRT

- Economical hybrid protection
- Smooth durable polishing finish
- Compatible over most bottom paints



COPPER-FREE ANTIFOULING PAINT

Pettit ECO HRT® copper-free antifouling uses the latest technology available to create a hybrid paint film strong enough to handle the tough marine environment without building up over time. Hybrid Reactive Technology features high density biocide utilization to maximize effectiveness by using biocide more effectively along with film modifiers to reduce yearly build-up, maintain uniform color consistency, and lower weight while providing a smoother finish than traditional paints.

ECO HRT smooth durable paint surface wears away over time, eliminating paint film build up and the need for sanding. This copper-free formula can be safely applied to all aluminum-hulled boats. It provides excellent antifouling protection and can be hauled and re-launched without any loss of effectiveness.



BLUE
1200



BLACK
1800



PONTOON GRAY
1300

Note: Color differences may occur between actual color chips shown.

***NEW* - BLACK 1800 NOW AVAILABLE IN NEW PACK SIZE - AEROSOL**

TECHNICAL INFORMATION

FINISH: Eggshell

SOLIDS BY VOLUME: 55%

SOLIDS BY WEIGHT: 58%

COVERAGE: Liquid 500ft²/gal.
Aerosol **15ft²**

VOC: 330 grams/liter (*as supplied*)

BIOCIDE: ECONEA™...6%
Zinc Pyrithione...4.8%

FLASH POINT: 105°F (SETA)

APPLICATION METHOD: Brush, roller, aerosol, airless or conventional spray

MAXIMUM ROLLER THICKNESS: 3/16"

NUMBER OF COATS: 1 minimum per season with additional coats for extended service

WET FILM THICKNESS: 2.7 mils

DRY FILM THICKNESS: 1.5 mils

APPLICATION TEMP: 50°F Min / 90°F Max

THINNER: 120 Brushing Thinner
121 Spraying Thinner

DRY TIME: Minimum time in hours

TO RECOAT TO LAUNCH

90°F	1	2
70°F	2	4
50°F	4	8

The above dry times are minimums. There is no maximum dry time before launching.

The active ingredients in ECO HRT can settle over time, especially if the paint has been on the shelf for several months. It is necessary to thoroughly mix the paint before using. If possible, shake the can of paint on a mechanical paint shaker. Before using, check the sides and bottom of the can to make sure all of the pigment has been mixed in. If mixing is going to be done with a wooden paddle or an electric drill mixer, pour off half of the liquid from the top of the can into another can and then properly mix in any settled pigment; then remix the two parts together thoroughly.

Adhere to all application instructions, precautions, conditions, and limitations to obtain optimum performance. Refer to individual labels and tech sheets for detailed instructions when using associated products, etc.

When spraying, do not thin ECO HRT more than 5% (6 ounces per gallon) or inadequate paint film thickness will occur, and premature erosion of the finish will be likely. Do not apply ECO HRT in thick films or in more than two coats, as poor adhesion may result. When applying by roller, use a short nap (3/16" maximum) roller.

COATING PERFORMANCE, IN GENERAL, IS PROPORTIONAL TO THE DEGREE OF SURFACE PREPARATION. FOLLOW ALL RECOMMENDATIONS VERY CAREFULLY, AVOIDING ANY SHORTCUTS.



APPLICATION SYSTEMS: ECO HRT is easily applied by brush, roller or spray. When rolling, use only a high-quality short nap (maximum 3/16" nap) roller cover. Apply using thin coats. Mix paint thoroughly to ensure ingredients are evenly dispersed throughout the can. All surfaces must be clean, dry and properly prepared prior to painting.

PREVIOUSLY PAINTED SURFACES: ECO HRT may be applied over most aged hard and abrasive antifouling coatings. Consult the Pettit Antifouling Compatibility Chart for specific recommendations. Old tin copolymers must be removed completely or sealed with Pettit 6627 Tie-Coat Primer before applying this product. The paint systems outlined below contain references to other products; please read and understand the label and/or Technical Bulletin for these products as well, to ensure that they are used properly. If the previous coating is in good condition, thoroughly sand with 80-grit sandpaper then solvent clean with Pettit 120 Brushing Thinner to remove residue. Apply two thin finish coats of ECO HRT. If the previous coating is soft or in poor condition, remove to the bare surface by sanding or using EZ Speed Strip™ 125. Proceed with appropriate bare system as described below.

BARE FIBERGLASS: All bare fiberglass, regardless of age, should be thoroughly cleaned with Pettit 92 Bio-Blue® Hull Surface Prep or de-waxed several times with Pettit D95 Dewaxer. Proceed with either Sanding Method or one of the Non-Sanding Methods below.

SANDING METHOD: After the surface has been de-waxed, sand thoroughly with 80-grit production paper to a dull, frosty finish and rewash the sanded surface with Pettit 120 Brushing Thinner to remove sanding residue. Then apply two thin coats of ECO HRT, following application instructions. Careful observation of application instructions will help ensure long-term adhesion of this and subsequent years' antifouling paint.

NON-SANDING METHOD: To eliminate the sanding method, thoroughly clean, de-wax, the surface with Pettit 92 Bio-Blue Hull Surface Prep using a medium Scotch-Brite® pad. Thoroughly rinse all residue from the surface and let dry. Apply one coat of Pettit Protect® High Build Epoxy Primer (4700/4701 or 4100/4101). Consult the primer label for complete application and antifouling top-coating instructions. Apply two thin coats of ECO HRT. See Pettit Protect User Manual for complete detailed instructions.

BARRIER COAT: Fiberglass bottoms potentially can form osmotic blisters within the gelcoat and into the laminate. Prepare the fiberglass surface as mentioned above (sanding method) then apply two - three coats of Pettit Protect High Build Epoxy Primer (4700/4701 or 4100/4101), per label directions. Apply two thin coats of ECO HRT. See Pettit Protect User Manual for complete detailed instructions.

BLISTERED FIBERGLASS: See Pettit Protect User Manual for complete detailed instructions.

BARE WOOD: Bare wooden hulls should be sanded thoroughly with 80-grit sandpaper and wiped clean of sanding residue using Pettit 120 Brushing Thinner. A coat of Pettit 6627 Tie-Coat Primer thinned 25% with Pettit 97 Epoxy Thinner should be applied directly to the bare wood. Allow to dry four hours. Apply two thin coats of ECO HRT. Previously painted wood hulls should be thoroughly sanded. If priming is necessary on bare wood spots, apply a touch-up coat of Pettit 6627 Tie-Coat Primer thinned 25% with Pettit 97 Epoxy Thinner to these areas. Apply two thin finish coats of ECO HRT.

BARE STEEL AND CAST IRON*: Clean off grease or dirt. Remove loose rust and scale from the metal surface by sandblasting or wire brushing to 2-3 mil profile. Immediately clean the surface using a vacuum or fresh air blast. Apply two coats of Pettit 6980 Rustlok® Steel Primer, allowing each to dry only one to two hours prior to over-coating. Follow by two coats of Pettit Protect High Build Epoxy Primer (4700/4701 or 4100/4101), per label directions. If fairing is required, apply Pettit 7050 EZ-Fair Epoxy Fairing Compound between the two coats of Pettit Protect High Build Epoxy Primer. Apply two thin finish coats of ECO HRT. See Pettit Protect User Manual for complete detailed instructions.

MAINTENANCE: No antifouling paint can be effective under all conditions of exposure. Man-made pollution and natural occurrences can adversely affect antifouling paint performance. Extreme hot and cold-water temperatures; silt, dirt, oil, brackish water and even electrolysis can ruin an antifouling paint. Therefore, we strongly suggest that the bottom of the boat be checked regularly to make sure it is clean and that no growth is occurring. Lightly clean the bottom with a sponge or cloth to remove anything from the antifouling paint surface. Cleaning is particularly important with boats that are idle for extended period of time.

STAY CONNECTED

SEARCH **PETTIT PAINT** ON SOCIAL MEDIA PLATFORMS TO STAY CONNECTED WITH US.



WWW.PETTITPAINT.COM  (800) 221-4466

STAINLESS STEEL, BRONZE, LEAD AND NON-ALUMINUM ALLOYS*: Solvent clean, abrade to clean bright metal by sanding with 60-80 grit sandpaper, sandblasting or wire brushing. Apply 2-3 coats of Prop Coat Barnacle Barrier 1792 followed by 2 thin coats of ECO HRT.

AEROSOL APPLICATION INFORMATION: Shake can vigorously for at least two minutes after mixing balls begin to rattle. Shake often during use. Hold can upright 8 - 12 inches from the surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. Apply in thin coats. Allow no more than 5 minutes between two or three thin coats, otherwise allow to dry one hour before applying additional coats. When finished spraying, clear spray valve by turning can upside down and spraying until no more paint comes out. If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick a pin or other object in the stem.

BARE ALUMINUM: For maximum corrosion resistance, sandblast to clean, bright metal and remove blasting residue with clean, dry compressed air or a clean brush. Immediately apply one to two coats of Pettit 4400/4401 Aluma Protect Epoxy Primer, followed by two coats of Pettit Protect High Build Epoxy Primer (4700/4701 or 4100/4101), per label directions. Apply two thin finish coats of ECO HRT.

*These are simplified systems for small areas. Consult your Pettit representative of the Pettit Technical Department for more complex, professional systems. Always read the labels or tech sheets for all products specified herein before using.